

Department of Mechanical & Materials Engineering

Nedlands, Western Australia 6907

Telephone:

08 9380 3133

Facsimile:

08 9380 1024

Email:

nlaxton@cyllene.uwa.edu.au

Name:

Nigel Laxton MIEAust CPEng MIM

Position:

Senior Engineer

## SOLAR MATERIALS TESTING LABORATORY

11 January 1999

Emittance Tests ASTM E 408

Sample submitted by Gavin Batty

Emittance = 0.90

Tests carried out using Gier Dunkle DB100 Infra-red Reflectometer.

Solar Reflectance Tests

Sample submitted by Gavin Batty

Reflectance = 89%

Tests carried out using GBC Scientific Equipment Ltd. Reflectometer

Nigel Laxton